

6-1-1993

90 K TI-Ba-Ce-Cu-O superconductor and processes for making same

J. H. Wang

Zhengzhi Sheng
University of Arkansas, Fayetteville

Allen M. Hermann
University of Arkansas, Fayetteville

Follow this and additional works at: <https://scholarworks.uark.edu/pat>

Citation

Wang, J. H., Sheng, Z., & Hermann, A. M. (1993). 90 K TI-Ba-Ce-Cu-O superconductor and processes for making same. *Patents Granted*. Retrieved from <https://scholarworks.uark.edu/pat/234>

This Patent is brought to you for free and open access by ScholarWorks@UARK. It has been accepted for inclusion in Patents Granted by an authorized administrator of ScholarWorks@UARK. For more information, please contact scholar@uark.edu.



US005215962A

United States Patent [19]

[11] Patent Number: **5,215,962**

Wang et al.

[45] Date of Patent: **Jun. 1, 1993**

[54] **90 K TL-BA-CE-CU-O SUPERCONDUCTOR AND PROCESSES FOR MAKING SAME**

[75] Inventors: **J. H. Wang, Boulder, Colo.; Zhengzhi Sheng, Fayetteville, Ark.; Allen M. Hermann, Golden, Colo.**

[73] Assignee: **The University of Arkansas, Little Rock, Ark.**

[21] Appl. No.: **782,868**

[22] Filed: **Oct. 15, 1991**

Related U.S. Application Data

[63] Continuation of Ser. No. 484,844, Feb. 26, 1990, abandoned.

[51] Int. Cl.⁵ **C04B 41/89; H01L 39/12**

[52] U.S. Cl. **505/1; 505/783; 501/123; 501/152; 252/518; 252/521**

[58] Field of Search **505/783, 1; 501/123, 501/152; 252/518, 521**

[56] References Cited

U.S. PATENT DOCUMENTS

4,755,493	7/1988	Takeuchi et al.	501/134
4,870,052	9/1989	Engler et al.	505/1
4,880,773	11/1989	Itozaki et al.	505/1
4,994,432	4/1991	Hermann et al.	505/783

FOREIGN PATENT DOCUMENTS

0280812	9/1988	European Pat. Off.	.
0284062	9/1988	European Pat. Off.	.
0286289	10/1988	European Pat. Off.	.
0292340	11/1988	European Pat. Off.	.
0301952	2/1989	European Pat. Off.	.
0301958	2/1989	European Pat. Off.	.
0316009	5/1989	European Pat. Off.	.
236794	10/1988	Japan	.

OTHER PUBLICATIONS

Saito et al., "High- T_c Superconducting Properties in $(Y_{1-x}Tl_x)Ba_2Cu_3O_{7-x}$..." *Physica* 148B, 1987, 336-338.

Wang et al., "The 90k bulk superconductivity in the Thallium-Barium-Cerium-Copper-Oxygen System", *Physica C* 158(3) pp. 507-510, 1989.

Zhang et al., "The copper valence state and structure of lithium, cerium, europien, vanadium-doped ytthium-barium-copper-oxide system", *Mod. Phy. Lett. B*, 3(12), 955-60, 1989 abstract.

Sheng et al., "Superconductivity in the rare-earth-free Tl-Ba-A-O System above liquid-nitrogen temperature", *Nature*, vol. 332(3) 3 Mar. 1988.

Wu et al., "Bulk Superconductivity with T_c O up to 95K in a Tl-Pb-Ca-Ce-Sr-Cu-O with a $YBa_2Cu_3O_y$ -like structure", *Appl. Phys. Lett* 54(24) 2464-6 1989 (abstract).

Rao et al., "Superconductivity (1:1:2:2)-type layered cuprates of the formula $TlCa_{1-x}T_xSr_2Cu_2O_y$ (T-Yr rare earth element) *Physical Review* vol. 40 #4, 2565-67 Aug. 1, 1989.

Inoue et al., "Superconductivity in a Tl-Sr-Y-Cu-O System" *Jap. Jour Appl Phys.* vol. 28 #8, 1375-77 Aug. 1989.

Gangichi et al., "Superconductivity in Bi-Ca-Y-Si-Ca-O ac Tl-Ca-Y-Ba-Ci-O" *Mat'l Res Bull* vol. 24, pp. 103-109 Jan. 1989.

Wang et al., "the 90K bulk superconductivity in the thallium-barium-cerium-copper-oxygen system", *Physica C*, 158(3), pp. 507-510, 1989-abstract & comp search.

Sheng et al, "Superconductivity in the R-Tl-Sr-Cu-O system with R-Rare Earth", *Solid State Comm.*, vol. 71, #9, pp. 739-741, 1989.


(List continued on next page.)

Primary Examiner—Mark L. Bell
Assistant Examiner—C. M. Bonnar
Attorney, Agent, or Firm—Hermann Ivester

[57] ABSTRACT

A high temperature superconductor system having the nominal composition: Tl-Ba-Ce-Cu-O. The high temperature superconductor of the present invention has a transition temperature of about 90 K. Processes for making the high temperature superconductor are also provided.

19 Claims, 4 Drawing Sheets



OTHER PUBLICATIONS

- Hasegawa, T., et al., *High T_c Superconductivity of (La_{1-x}Sr_xCuO₄-Effect of Substitution . . . Superconductivity*, Japan Journal of Applied Physics, vol. 26, No. 4, Apr. 20, 1987, L337-L338.
- Kishio, K., et al., *Effect of Lanthanide Ion Substitutions for Lanthanum Sites on Superconductivity of (La_{1-x}Sr_x)₂CuO_{4-δ}*-Japanese Journal of Applied Physics, vol. 26, No. 4, Apr. 20, 1987, L391-L393.
- Ohshima, S., et al., *Superconducting and Structural Properties of the New Ba_{1-x}Ln_xCuO_{3-y} Compound System (Ln=La, Ce, Pr, Nd, Sm, Eu, . . . and Yb)*, Japanese Journal of Applied Physics, vol. 26, No. 5, May 1987, L815-L817.
- Tsurumi, S., et al., *High T_c Superconductivities of A₂Ba₄Cu₆O_{14+y}*-Japanese Journal of Applied Physics, vol. 26, No. 5, May 1987, L856-L857.
- Superconductivity News, vol. 1, No. 2, Aug. 1987, pp. 1, 2, and 6-8.
- Yang, K. N., et al., *High Temperature Superconductivity in Rare-Earth (R)-Barium Copper Oxides (RBa₂Cu₃O_{9-δ})*, Solid State Communications, vol. 63, No. 6, 1987, pp. 515-519.
- Tarascon, J. M., et al., *Oxygen and Rare-Earth Doping of the 90-K Superconducting Perovskite YBa₂Cu₃O_{7-x}*, Physical Review B, vol. 36, No. 1, 1987, 226-234.
- Hor, P. H., et al., *Superconductivity Above 90 K in the Square-Planar Compound System ABa₂Cu₃O_{6+x} with A=Y, La, Nd, Sm, Eu, Gd, Ho, Er, and Lu*, Physical Review Letters, vol. 58, No. 18, 1987, 1891-1894.
- Khurana, A., *Superconductivity Seen Above the Boiling Point of Nitrogen*, Physics Today, Apr. 1987, 17-23.
- Cava, R. J., et al., *Bulk Superconductivity at 91 K in Single-Phase Oxygen-Deficient Perovskite Ba₂YC₃O_{9-δ}*, Physical Review Letters, vol. 58, No. 16, 1987, 1676-1679.
- Nagashima, T., et al., *Superconductivity in Tl_{1.5}SrCaCu₂O_x*, Japanese Journal of Applied Physics, vol. 27, No. 6, Jun. 1988, L1077-L1079.
- Saito, T., et al., *High-T_c Superconducting Properties in (Y_{1-x}Tl_x)Ba₂Cu₃O_{7-y}, Y(Ba_{1-x}K_x)₂Cu₃O_{7-y} and YBa₂(Cu_{1-x}Mg_x)₃O_{7-y}*, Physica 148B, 1987, 336-338.
- Kondoh, S., et al., *Superconductivity in Tl-Ba-Cu-O System*, Solid State Communications, vol. 65, No. 11, 1988, 1329-1331.
- Sera, M. et al., *On the Structure of High-T_c Oxide System Tl-Ba-Cu-O*, Institute for Molecular Science, Myodaiji, Okazaki 444 Japan, 1988, Feb.
- Ihara, H. et al., *Possibility of Superconductivity at 65° C. in Sr-Ba-Y-Cu-O System*, Japanese Journal of Applied Physics, vol. 26, No. 8, Aug. 1987, L1413-L1415.
- Ishida, T., *Compositional Variation of High T_c in Yb₂Er_{1-x}Ba₂Cu₃O_{6+y} System*, Japanese Journal of Applied Physics, vol. 26, No. 8, Aug. 1987, L1294-L1295.
- Kijima, T., et al., *Superconductivity in the Bi-Sr-La-Cu-O System*, Japanese Journal of Applied Physics, vol. 27, No. 6, Jun. 1988, L1035-L1037.
- Richert, B., et al., *Atomic Substitution in YBa₂Cu₃O₇: Modification of the Electronic Structure*, American Institute of Physics Conference Proceedings No. 165 (Thin Film Processing and Characterization of High-Temperature Superconductors), Nov. 6, 1987, 277-283.
- Ferreira, J. M., et al., *Long-range Magnetic Ordering the High-T_c Superconductors RBa₂Cu₃O_{7-δ} R=Nd, Sm, Gd, Dy and Er)*, Physical Review B, vol. 37, Nov. 4, Feb. 1, 1988, 2368-2371.
- Shih, I., et al., *Multilayer Deposition of Thallium Barium Calcium Copper Oxide Films*, Applied Physics Letter 53(6), 1988, 523-525.
- Ginley, D. S., et al., *Sequential Electron Beam Evaporated Films of Tl₂CaBa₂Cu₂O_y with Zero resistance at 97 K*, Applied Physics Letters, 53 (5), Aug. 1, 1988, 406-408.
- Qiu, C. X., et al., *Formation of Tl-Ca-Ba-Cu-O Films by Diffusion of Tl into rf-sputtered Ca-Ba-Cu-O*, Applied Physics Letters, 53 (12), Sep. 19, 1988, 1122-1124.
- Gopalakrishnan, I. K., et al., *Synthesis and Properties of a 125 K Superconductor in the Tl-Ca-Ba-Cu-O System*, Applied Physics Letters, 53 (5), Aug. 1, 1988, 414-416.
- Parkin, S. S. P., et al., *Bulk Superconductivity at 125 K in Tl₂Ca₂Ba₂Cu₃O_x*, Physical Review, Jun. 1988, 2539-2542.
- Sheng, Z. Z., et al., *Superconductivity at 90 K in the Tl-Ba-Cu-O System*, Physical Review Letters, vol. 60, No. 10, Mar. 7, 1988, 937-940.
- Sheng, Z. Z., et al., *Bulk Superconductivity at 120 K in the Tl-Ca/Ba-Cu-O System*, Nature, vol. 332, Mar. 10, 1988, 138-139.
- Ihara, H., et al., *A New High-T_c TlBa₂Ca₃Cu₄O₁₁ Superconductor with T₂>120 K*, Nature, vol. 334 11 Aug. 1988, 510-511.

(List continued on next page.)

OTHER PUBLICATIONS

- Sheng, Z. Z., et al., *Tl₂O₃ Vapor Process of Making Tl-Ba-Ca-Cu-O Superconductors*, Appl. Phys. Lett. 53 (26), 26 Dec. 1988, 2686-2688.
- Hazen, R. M., et al., *100-K Superconducting Phases in the Tl-Ca-Ba-Cu-O System*, Physical Review Letters, vol. 60, Mo. 16, 18 Apr. 1988, 1657-1660.
- Sheng, Z. Z., et al., *New 120 K Tl-Ca-Ba-Cu-O Superconductor*, Appl. Phys. Lett., vol. 52, No. 20, 16 May 1988, 1738-1740.
- Lin, R. J., et al., *Forming Superconducting Tl-Ca-Ba-Cu-O Thin Films by the Diffusion Method*, Japanese Journal of Applied Physics, vol. 28, No. 1, Jan. 1989, L85 L85-L87.
- Thompson, B. J., et al., *Preparation of High T_c Tl-Ba-Ca-Cu-O Thin Films by Pulsed Laser Evaporation and Tl₂O₃ Vapor Processing*, Appl. Phys. Lett. 54(18), 1 May 1989, 1810-1811.
- Sugise, R., et al., *Preparation Tl₂Ba₂Ca₂Cu₃O₄ Thick Films from Ba-Ca-Cu-O Films*, Japanese Journal of Applied Physics, vol. 27, No. 12, Dec. 1988, L2314-L2316.
- Hatta, S., et al., *Pt-coated Substrate Effect on Oxide Superconductive Films in Low-Temperature Processing*, Appl. Phys. Lett. 53 (2), 11 Jul. 1988, 148-150.
- Lee, W. Y., et al., *Superconducting Tl-Ca-Ba-Cu-O Thin Films With Zero Resistance at Temperatures of up to 120 K*, Appl. Phys. Lett. 53 (4), 25 Jul. 1988, 329-331.
- Oota, A., et al., *Electrical, Magnetic and Superconducting Properties of High-T_c Superconductor (Y, Sc)-(Ba, Sr)-Cu Oxide*, Japanese Journal of Appl Physics, vol. 26, No. 8, Aug. 1987, L1356-1358.
- Iwazumi, T., et al., *Identification of a Structure with Two Superconducting Phases in L-Ba-Cu-O System (L=La or Y)*, Japanese Journal of Applied Physics, vol. 26, No. 5, May, 1987, L621-L623.
- Capone, II., D. W., et al., *Super Critical Fields and High Superconducting Transition Temperatures of La_{1.85}Sr_{0.15}CuO₄ and La_{1.85}Ba_{0.15}CuO₄*, Appl. Phys. Lett 50 (9), 2 Mar., 1987, 543-544.
- Johnson, D. W., et al., *Fabrication of Ceramic Articles from High T_c Superconducting Oxides*, Materials Research Society, Symposium S Proceedings (High Temperature Superconductors), Apr. 1987, 193-195.
- Garwin, L., *Superconducting Conference Yields New Temperature Record*, Nature vol. 332 10 Mar. 1988.
- Suzuki, A., et al., *Rare-Earth(RE)-Barium Solubility Behavior in y(Ba_{z-x}RE_x)Cu₃O_{7+δ} and Sm(Ba_{z-x}RE_x)Cu₃O_{7+δ}*, Japanese Journal of Applied Physics, vol. 27, No. 5, May, 1988, L792-L794.
- Nagashima, T., et al., *Improving Superconducting Characteristics of Tl-Sr-Ca-Cu-O by Doping with Pb and/or Rare-Earth elements*, Japanese Journal of Applied Physics, vol. No. 6, Jun. 1989, L930-L933.
- Vijayaraghaven, R., et al., *Investigations of Novel Cuprates of the TlCa_{1-x}Ln_xSr₂Cu₂O_{7-δ} (n=rare earth) Series Showing Electron-or Hole-superconductivity Depending on the Composition*, Superconducting Science and Technology, vol. 2(3), Sep. 1989, 195-201.
- Peters, P. N., et al., *Observation of Enhanced Properties in Samples of Silver Oxide Doped YBa₂Cu₃O_x*, Appl. Phys. Lett 52 (24), 13 Jun. 1988, 2066-2067.
- S. Natarajan et al., *Superconductivity Studies on (Y_{1-x}Ln_x)Ba₂Cu₃O₇, Ln=La, Pr,Tb*, Physica C, vol. 153-155, Feb. 1988, 926-927.
- D. D. Sarma, et al., *Electronic Structure of High-T_c Superconductors from Soft-x-ray Absorption*, Physical Review B, vol. 37, No. 16, Jun. 1988, 9784-9787.
- K. Kishio, et al., *Superconductivity Achieved at Over Liquid Nitrogen Temperature by (mixed Rare Earths)-Ba-Cu Oxides*, Japanese Journal of Applied Physics, vol. 26 No. 5, May 1987, L694-L696.
- Waldrop, M. Mitchell, *Thallium Superconductor Reaches 125K*, Research News, Mar. 1988, 1243.
- Qadri, S. B., et al., *x-ray Identification of the Superconducting High-T_c Phase in the Y-Ba-Cu-O systems*, Physical Review B, vol. 35, No. 13, 1987.
- Murphy, D. W., et al., *New Superconducting Cuprate Perovskites*, Physical Review Letters, vol. 58, May 1987, 1888-1890.

FIG.1




FIG. 2




FIG. 3





FIG.4



90 K Tl-Ba-Ce-Cu-O SUPERCONDUCTOR AND PROCESSES FOR MAKING SAME

This is a continuation of application Ser. No. 484,844, filed Feb. 26, 1990, now abandoned.

BACKGROUND OF THE INVENTION

The present invention relates generally to high temperature superconductors. More specifically, the present invention relates to Tl-Ba-Ce-Cu-O superconductors and processes for making same.


Tl-Ba-Cu-O and Tl-Ba-Ca-Cu-O superconducting systems have been identified. U.S. patent application Ser. No. 144,114 and Ser. No. 155,247, now U.S. Pat. No. 4,962,083, issued Oct. 9, 1990 filed in the name of Hermann and Sheng, two of the three inventors of the present invention, disclose, in part, Tl-Ba-Cu-O and Tl-Ba-Ca-Cu-O superconductor systems. The discovery of the Tl-Ba-Cu-O and Tl-Ba-Ca-Cu-O superconducting systems has led to the identification of a number of Tl-based superconducting compounds, including the series $Tl_mBa_2Ca_{n-1}Cu_nO_{1.5m+2n+1}$, wherein $m=1-2$ and $n=1-5$.

One of the phases of the Tl-Ba-Ca-Cu-O system that has been identified is the $Tl_2Ba_2Ca_2Cu_3O_{10}$ superconductor phase. This phase has a transition temperature of 125 K., which transition temperature, the inventors of the present invention believe, is the highest to date among existing high temperature superconductors.

The presently known phases of such high T_c superconductors have a tetragonal structure and are p-type. These superconductive phases are also anisotropic. If a new superconductor system was discovered that had a different structure, it could be used for several special applications.

SUMMARY OF THE INVENTION

The present invention provides a new superconductor system and method for making same. To this end, the present invention provides a high temperature superconductive system containing thallium (Tl), barium (Ba), cerium (Ce), copper (Cu), and oxygen (O):



In a preferred embodiment of the present invention, the superconductive system of the present invention has the following approximate stoichiometry:



wherein:

$$1.1 \leq a \leq 2.2;$$

$$1.8 \leq b \leq 2.2;$$

$$0.5 < c < 1.5$$

$$1.1 \leq d \leq 4; \text{ and}$$

$$5.55 < e < 12.5.$$

In an embodiment of the present invention, the superconductor has a nominal composition of $Tl_{2.2}Ba_2CeCu_3O_{10.3}$ and is superconducting at 90 K.

A method of producing the high temperature superconductors is also provided. The method of the present invention allows the superconductor to be prepared at temperatures of approximately 900° to about 925° C. in flowing oxygen. Accordingly, the method of the present invention allows the superconductor to be formed at relatively low temperatures. Furthermore, the method of the present invention allows the superconductor to

be produced rapidly, in that it need only be heated for approximately 3 to about 5 minutes.

Accordingly, it is an advantage of the present invention to provide a new superconductor composition.

It is a further advantage of the present invention to provide a new method for making superconductors.

Additional advantages and features of the present invention are described in, and will be apparent from, the detailed description of the presently preferred embodiments and from the drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a graph of resistance verses temperature of two nominal $Tl_{2.2}Ba_2CeCu_3O_{10.3}$ samples of the present invention.

FIG. 2 illustrates a graph of $R(T)/R(200)$ as a function of temperature for nominal $Tl_{2.2}Ba_2Ce_xCu_3O_y$ samples of the present invention, wherein $x=0.1, 0.5, 1.0$ and 1.5 .


FIG. 3 illustrates a graph of the ac susceptibility as a function of temperature for two nominal $Tl_{2.2}Ba_2CeCu_3O_{10.3}$ samples of the present invention.

FIG. 4 illustrates the powder x-ray diffraction patterns of nominal $Tl_{2.2}Ba_2Ce_xCu_3O_y$ samples of the present invention, wherein $x=0.1, 0.5, 1.0$ and 1.5 .

DETAILED DESCRIPTION OF THE PRESENTLY PREFERRED EMBODIMENT

The present invention provides a new high temperature superconductor system and method of making same. As used herein, the term "high temperature" refers to a temperature above the boiling point of liquid nitrogen.

The superconductor system of the present invention has the following general formula:



In an preferred embodiment of the present invention, a superconductor constructed from the new superconductive system of the present invention has the following approximate stoichiometry:



wherein:

$$1.1 \leq a \leq 2.2;$$

$$1.8 \leq b \leq 2.2;$$

$$0.5 < c < 1.5$$

$$1.1 \leq d \leq 4; \text{ and}$$

$$5.55 < e < 12.5.$$

The TlBaCeCuO system is superconducting at 90 K.

In an embodiment, the superconductor composition of the present invention has a nominal composition $Tl_{2.2}Ba_2CeCu_3O_{10.3}$.

By the way of example and not limitation, examples of the new high temperature Tl-Ba-Ce-Cu-O superconductor of the present invention, and method of making same, will now be set forth.

EXAMPLE

A. The following reagents were utilized:

1. Tl_2O_3 ,
2. BaO_2 ,
3. CeO_2 ,
4. CuO .

B. The following procedure was followed:

1. Tl_2O_3 , BaO_2 , CeO_2 , and CuO were completely mixed in a molar ratio of 1.1:2:1:3.
2. The mixture was then completely ground and pressed into a pellet having a diameter of 7 mm and a thickness of approximately 1 to about 2 mm.
3. The pellet was placed in an alumina crucible.
4. The crucible and its content were placed into a tube furnace which had been heated to a temperature of approximately 900° to about 925° C. The crucible and its content were then heated in flowing oxygen for approximately 3 to about 5 minutes.
5. The crucible and its content were then furnace cooled.

Nominal $Tl_{2.2}Ba_2CeCu_3O_{10.3}$ samples prepared using this procedure, proved to be superconducting at 90 K. The samples had a dark grey color and were dense. The superconducting behavior of the samples was sensitive to both heating temperature and heating duration. Quenching of the samples depressed T_c only slightly.

FIG. 1 illustrates graphically resistance verses temperature for two nominal $Tl_{2.2}Ba_2CeCu_3O_{10.3}$ samples made pursuant to the procedure of this example. The two samples were made in different batches. The resistance was measured by a standard four-probe technique with silver paste contacts. Both resistance and ac susceptibility data were taken in a commercial ADP closed-cycle refrigerator with computer-control and processing.

As illustrated in FIG. 1, sample A had an onset temperature of 95 K., a mid-point temperature of 88 K., and a zero resistance temperature of 83 K. Sample B had an onset temperature of 90 K., a mid-point temperature of 85 K. and a zero resistance temperature of 80 K.

FIG. 2 illustrates graphically $R(T)/R(200)$ as a function of temperature for a series of samples with a starting composition of $Tl_{2.2}Ba_2Ce_xCu_3O_y$, where $x=0.1, 0.5, 1.0$ and 1.5 . As illustrated in FIG. 2, the samples with a value of $x=0.1, 0.5$, and 1.5 all had a T_c of about 20 K. As illustrated, only the sample with the intermediate value of $x=1.0$ was superconducting at 90 K. Therefore, the formation of a 90 K. superconducting phase of Tl-Ba-Ce-Cu-O has a strong dependence on the Ce concentration.

FIG. 3 illustrates graphically ac susceptibility verses temperature of the samples of FIG. 1. As the figure illustrates, the samples exhibit a diamagnetism onset at about 90 K., which is consistent with their superconducting transition temperatures measured resistively. The ac susceptibility signal decreases with decreasing temperature and does not saturate down to 15 K. In the present example, the signal at 15 K. was about 10-20% of that of a good quality Tl-Ba-Ca-Cu-O sample. Thermoelectric power determinations, from room temperature down to near the superconducting transition temperature, show n-type behavior for the sample of this example.

A powder x-ray diffraction analysis was used to attempt to identify the phase responsible for the 90 K. superconductivity. The powder x-ray diffraction was done for a number of Tl-Ba-Ce-Cu-O samples and a number of related samples. Powder x-ray diffraction studies were performed with $Cu K\alpha$ and radiation with the use of a DIANO DTM 1057 diffractometer. FIG. 4 illustrates the powder x-ray diffraction patterns for the samples of FIG. 2.

In general, the diffraction patterns of the Tl-Ba-Ce-Cu-O samples can be assigned to one of three phases: unreacted CuO ; tetragonal $Tl_2Ba_2CuO_6$; and an un-

known phase. In FIG. 4, the diffraction pattern of the unknown phase can be indexed to a cubic structure with lattice parameter of 4.400 A, which is very close to the lattice parameter of 4.386 A of the cubic $BaCeO_3$. This is omitting the $2\theta=25^\circ$ peak in the figure.


If the 28.7° peak is assigned to the unidentified phase and assuming that the 30.0° peak represents the tetragonal, $Tl_2Ba_2CuO_6$, the ratios of the unidentified phase to the $Tl_2Ba_2CuO_6$ phase are 0.5 for $x=0.1$, 1.5 for $x=0.5$, 5 for $x=1.0$, and 6 for $x=1.5$, respectively.

All four samples consist primarily of the two phases, but only the sample with $x=1.0$ is superconducting at 90 K. The inventors believe that if the $Tl_2Ba_2CuO_6$ phase is responsible for the 90K superconductivity, it, most probably, has been doped by Ce, and if the unidentified phase is responsible for the 90K superconductivity, it must consist of all four metallic elements, Tl, Ba, Ce, and Cu.

It should be understood that various changes and modifications to the presently preferred embodiments described herein will be apparent to those skilled in the art. Such changes and modifications can be made without departing from the spirit and scope of the present invention and without diminishing its attendant advantages. It is therefore intended that such changes and modifications be covered by the appended claims.

We claim:

1. A superconductor having the composition:



2. A superconductor having the following approximate stoichiometry:



wherein:

- $$1.1 \leq a \leq 2.2;$$
- $$1.8 \leq b \leq 2.2;$$
- $$0.5 < c < 1.5$$
- $$1.1 \leq d \leq 4; \text{ and}$$
- $$5.55 < e < 12.5.$$

3. A composition that is superconducting at 90 K. having the following approximate nominal stoichiometry:



4. A high temperature superconducting material including a $Tl_2Ba_2CuO_6$ phase that has been doped by Ce.

5. A superconductor having the general formula $TlBaCeCuO$ and a tetragonal $Tl_2Ba_2CuO_6$ phase.

6. A method for making a high temperature superconductor comprising the steps of:

- a) mixing Tl_2O_3 , BaO_2 , CeO_2 , and CuO ;
- b) heating the mixture in flowing O_2 ; and
- c) cooling the mixture.

7. The method of claim 6 wherein Tl_2O_3 , BaO_2 , CeO_2 , and CuO are mixed in a molar ratio of 1.1:2:1:3.

8. The method of claim 6 wherein the mixture is heated to a temperature of approximately 900° to about 925° C.

9. The method of claim 6 wherein the mixture, prior to being heated, is pressed into a pellet.

10. The method of claim 9 wherein the pellet is heated to a temperature of approximately 900° to about 925° C.

5

11. The method of claim 8 wherein the pellet is heated in a tube furnace and flowing oxygen at a temperature of approximately 900° to about 925° C.

12. The method of claim 8 wherein the pellet is heated in flowing O₂ for approximately 3 to about 5 minutes.

13. The method of claim 8 wherein the pellet is furnace cooled.

6

14. A method for making a high temperature superconductor including a Tl₂Ba₂CuO₆ phase comprising the steps of:

heating a TlBaCeCuO mixture in flowing oxygen.

5 15. The method of claim 14 wherein the TlBaCeCuO mixture is created by mixing Tl₂O₃, BaO₂, CeO₂, and CuO.

16. The method of claim 14 wherein the mixture is heated to approximately 900° to about 925° C.

10 17. The product of the process of claim 6.

18. The product of the process of claim 14.

19. The product of the process of claim 15.

* * * * *

15

20

25

30

35

40

45

50

55

60

65