

6-24-2014

Methods and apparatus for making coatings using electrostatic spray

Ajay P. Malshe

University of Arkansas, Fayetteville

Wenping Jiang

University of Arkansas, Fayetteville

Justin B. Lowrey

Follow this and additional works at: <http://scholarworks.uark.edu/pat>

Recommended Citation

Malshe, Ajay P.; Jiang, Wenping; and Lowrey, Justin B., "Methods and apparatus for making coatings using electrostatic spray" (2014). *Patents Granted*. 25.

<http://scholarworks.uark.edu/pat/25>

This Patent is brought to you for free and open access by ScholarWorks@UARK. It has been accepted for inclusion in Patents Granted by an authorized administrator of ScholarWorks@UARK. For more information, please contact scholar@uark.edu, ccmiddle@uark.edu.



US008758863B2

(12) **United States Patent**
Malshe et al.

(10) **Patent No.:** **US 8,758,863 B2**
(45) **Date of Patent:** **Jun. 24, 2014**

(54) **METHODS AND APPARATUS FOR MAKING COATINGS USING ELECTROSTATIC SPRAY**

(75) Inventors: **Ajay P. Malshe**, Springdale, AR (US);
Wenping Jiang, Fayetteville, AR (US);
Justin B. Lowrey, Fayetteville, AR (US)

(73) Assignees: **The Board of Trustees of the University of Arkansas**, Little Rock, AR (US); **NanoMech, Inc.**, Fayetteville, AR (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 659 days.

(21) Appl. No.: **12/446,031**

(22) PCT Filed: **Oct. 18, 2007**

(86) PCT No.: **PCT/US2007/022220**

§ 371 (c)(1),
(2), (4) Date: **Oct. 26, 2010**

(87) PCT Pub. No.: **WO2008/051433**

PCT Pub. Date: **May 2, 2008**

(65) **Prior Publication Data**

US 2011/0033631 A1 Feb. 10, 2011

Related U.S. Application Data

(60) Provisional application No. 60/852,931, filed on Oct. 19, 2006.

(51) **Int. Cl.**
B05D 1/06 (2006.01)
B05D 3/02 (2006.01)

(52) **U.S. Cl.**
USPC **427/475; 427/485; 427/486; 239/704**

(58) **Field of Classification Search**
USPC 427/475, 485, 486
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,985,297 A *	10/1976	Itoh	239/698
4,031,278 A	6/1977	Patel	
4,105,571 A	8/1978	Shaub et al.	
4,168,241 A	9/1979	Kozima et al.	
4,334,928 A	6/1982	Hara et al.	
4,715,972 A	12/1987	Pacholke	
4,745,010 A	5/1988	Sarin et al.	
4,842,893 A	6/1989	Yializis et al.	
4,877,677 A	10/1989	Hirochi et al.	
4,933,105 A *	6/1990	Fong	424/462
5,102,592 A	4/1992	McCauley et al.	

(Continued)

FOREIGN PATENT DOCUMENTS

JP	2004113931	4/2004
JP	2004160388	6/2004
JP	2005342657	12/2005


Primary Examiner — Frederick Parker

(74) *Attorney, Agent, or Firm* — J. Charles Dougherty

(57) **ABSTRACT**

Methods for creating coatings composed of a single material or a composite of multiple materials, beginning with ESC to deposit the base layer and then using other methods for the binding step beyond CVI. Also, for certain materials and applications, some pre-processing or pre-treatment of the coating materials is necessary prior to deposition in order to achieve a satisfactory coating. This application discloses methods for pre-deposition treatment of materials prior to ESC deposition. It also discloses methods for post-processing that provide additional functionality or performance characteristics of the coating. Finally, this application discloses certain apparatus and equipment for accomplishing the methods described herein.

27 Claims, 9 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

5,129,918	A	7/1992	Chattopadhyay	6,852,948	B1	2/2005	Harrison
5,273,790	A	12/1993	Herb et al.	6,861,088	B2	3/2005	Weber et al.
5,286,565	A	2/1994	Holzl et al.	6,864,201	B2	3/2005	Schultz et al.
5,328,875	A	7/1994	Ueda et al.	6,874,712	B2*	4/2005	Milojevic et al. 239/690
5,330,854	A	7/1994	Singh et al.	6,933,049	B2	8/2005	Wan et al.
5,363,821	A	11/1994	Rao et al.	6,933,263	B2	8/2005	Manka et al.
5,389,118	A	2/1995	Hinterman et al.	6,962,895	B2	11/2005	Scharf et al.
5,391,422	A	2/1995	Omori et al.	7,018,606	B2	3/2006	Tenne et al.
5,407,464	A	4/1995	Kaliski	7,018,958	B2	3/2006	Arrowsmith et al.
5,441,762	A	8/1995	Gray et al.	7,022,653	B2	4/2006	Hartley et al.
5,451,260	A	9/1995	Versteeg et al.	7,034,091	B2	4/2006	Schultz et al.
5,466,642	A	11/1995	Tajima et al.	7,052,532	B1	5/2006	Liu et al.
5,500,331	A	3/1996	Czekai et al.	7,060,319	B2	6/2006	Fredrickson
5,503,913	A	4/1996	Konig et al.	7,247,346	B1	7/2007	Sager et al.
5,534,808	A	7/1996	Takaki et al.	7,250,195	B1	7/2007	Storey et al.
5,614,140	A	3/1997	Pinneo	7,442,665	B2	10/2008	Schultz et al.
5,654,042	A*	8/1997	Watanabe et al. 427/459	2002/0176989	A1	11/2002	Knudsen et al.
5,677,060	A	10/1997	Terentieva et al.	2003/0003237	A1	1/2003	Seabaugh et al.
5,679,399	A	10/1997	Shlenker et al.	2003/0025014	A1	2/2003	Sun et al.
5,704,556	A	1/1998	McLaughlin	2003/0162179	A1	8/2003	Potyrailo et al.
5,711,489	A*	1/1998	Yanagida et al. 239/697	2003/0219544	A1	11/2003	Smith et al.
5,733,609	A	3/1998	Wang	2004/0018238	A1	1/2004	Shukla
5,766,783	A	6/1998	Utsumi et al.	2004/0038808	A1	2/2004	Hampden-Smith et al.
5,800,866	A	9/1998	Myers et al.	2004/0228963	A1	11/2004	Bergh et al.
5,830,813	A	11/1998	Yao et al.	2005/0064088	A1	3/2005	Fredrickson
5,834,689	A	11/1998	Cook	2005/0079200	A1	4/2005	Rathenow et al.
5,882,777	A	3/1999	Kukino et al.	2005/0123759	A1	6/2005	Weinberg et al.
5,889,219	A	3/1999	Moriguchi et al.	2005/0233062	A1	10/2005	Hossainy et al.
5,897,751	A	4/1999	Makowiccki et al.	2005/0244644	A1	11/2005	Hampden-Smith et al.
5,902,671	A	5/1999	Kutscher	2005/0266170	A1*	12/2005	Nesbitt 427/475
5,928,771	A	7/1999	DeWald, Jr. et al.	2006/0120947	A1	6/2006	Tenne et al.
5,945,166	A	8/1999	Singh et al.	2006/0177573	A1	8/2006	Pui et al.
5,985,356	A	11/1999	Schultz et al.	2006/0193890	A1	8/2006	Owens et al.
6,004,617	A	12/1999	Schultz et al.	2006/0198940	A1	9/2006	McMorrow
6,053,420	A*	4/2000	Ahlbert et al. 239/3	2006/0198941	A1	9/2006	Behan et al.
6,196,910	B1	3/2001	Johnson et al.	2006/0198942	A1	9/2006	O'Connor et al.
6,217,843	B1	4/2001	Homyonfer et al.	2006/0199013	A1	9/2006	Malshe et al.
6,240,873	B1	6/2001	Bertellotti et al.	2006/0219294	A1	10/2006	Yabuuchi et al.
6,258,139	B1	7/2001	Jensen	2006/0275542	A1	12/2006	Mehta et al.
6,258,237	B1	7/2001	Gal-Or et al.	2007/0003749	A1	1/2007	Asgari
6,276,618	B1*	8/2001	Yanagida et al. 239/693	2007/0004884	A1	1/2007	Bildstein
6,346,290	B1	2/2002	Schultz et al.	2007/0065668	A1	3/2007	Idei
6,368,665	B1	4/2002	Hunt et al.	2007/0154634	A1	7/2007	Renn
6,372,012	B1	4/2002	Majagi et al.	2007/0224239	A1	9/2007	Behan et al.
6,406,738	B1*	6/2002	Hogan et al. 427/2.14	2008/0029625	A1	2/2008	Talton
6,410,086	B1	6/2002	Brandon et al.	2008/0050450	A1	2/2008	Arnold et al.
6,484,826	B1	11/2002	Anderson et al.	2008/0066375	A1	3/2008	Roos et al.
6,540,800	B2	4/2003	Sherman et al.	2008/0166493	A1	7/2008	Xiao et al.
6,544,599	B1	4/2003	Brown et al.	2008/0280141	A1	11/2008	Dobbs et al.
6,607,782	B1	8/2003	Malshe et al.	2008/0305259	A1	12/2008	Saijo
6,756,119	B1	6/2004	Clough	2008/0311306	A1	12/2008	Xiao et al.
				2008/0312111	A1	12/2008	Malshe et al.

* cited by examiner




Fig. 1




Fig. 2




Fig. 3




Fig. 4





Fig. 5



- 1. *Spray Nozzle Assembly*
- 2. *Coating Chamber*
- 3. *Stage Suspension*
- 4. *Coating Stage*
- 5. *Powder Recycling Collector*

Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10

1

METHODS AND APPARATUS FOR MAKING COATINGS USING ELECTROSTATIC SPRAY

This application is the National Stage of International Application No.

PCT/US2007/022220, filed 18 Oct. 2007, which claims the benefit of U.S. Provisional Application No. 60/852,931, entitled "Methods and Apparatus for Making Coatings Using Electrostatic Spray," and filed on Oct. 19, 2006, both of which are incorporated herein by reference.

BACKGROUND OF THE INVENTION

The present invention relates to methods and apparatus for making coatings and articles from various material compositions involving use of electrostatic spray as the core method of coating deposition. These coatings may be used for a variety of applications, including as examples: abrasion-resistant coatings for cutting tools and wear parts, solid lubricant coatings for tools and wear parts, bio-friendly or biocidal coatings for biomedical implants, and thin film coatings for microelectronics, among others. Using the processes and equipment designs described in the detailed description section hereof, coatings may be applied to many different substrate materials and parts having simple or complex 3-dimensional geometries.

U.S. Pat. No. 6,607,782 issued Aug. 19, 2003 to Ajay P. Malshe, et al., disclosed a method that uses electrostatic spray coating (ESC) to deposit a base layer or preform on a substrate, followed by chemical vapor infiltration (CVI) to introduce a binder phase that creates a composite coating with good adherence of the binder to the initial phase particles and adherence of the composite coating to the substrate.

SUMMARY OF THE INVENTION

The present invention comprises additional methods for creating coatings composed of a single material or a composite of multiple materials, beginning with ESC to deposit the base layer and then using other methods for the binding step beyond CVI. ESC followed by CVI has been used successfully for creating composite coatings comprised of cubic boron nitride (cBN) and titanium nitride (TiN), on carbide substrates. However, because CVI exposes the substrate to high temperatures it is not suitable for certain materials that may be damaged or their properties degraded by the high temperature. Also, CVI as a binding step is not practical for applications involving very large surface areas due to the limited size of CVI reactors. Due to these and other limitations, we have devised additional means of applying a second phase to initial green coatings deposited using ESC. The new two-step coatings processes that result are disclosed in this application.

Also, for certain materials and applications, some pre-processing or pre-treatment of the coating materials is necessary prior to deposition in order to achieve a satisfactory coating. The invention in various embodiments comprises methods for pre-deposition treatment of materials prior to ESC deposition. It also comprises in various embodiments methods for post-processing that provide additional functionality or performance characteristics of the coating.

Finally, the invention in various embodiments comprises certain apparatus and equipment for accomplishing the methods described herein.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates the two-step coating process, including an initial deposition of a base or green coating layer, followed by a post-deposition treatment step.

2

FIG. 2 shows the case in which a pre-deposition treatment is applied to the coating materials prior to deposition.

FIG. 3 illustrates a fluidizer, used to separate dry powder particles, avoid agglomeration, and preferentially feed ultrafine particles to the deposition system.

FIG. 4 illustrates a jet mill, which helps de-agglomerate powders using aerodynamic forces.

FIG. 5 shows an aerosol spray used to de-agglomerate powders as they are fed to the deposition system.

FIG. 6 shows the deposition chamber used to contain the materials being deposited, preventing unacceptable release to the environment, allow for adjustment of spray gun to substrate distance, and capture and recycle of unused coating materials.

FIG. 7 illustrates a rotating stage used to ensure uniform deposition of the coating on the substrate.

FIG. 8 shows fluidization integrated with the deposition system including the chamber.

FIG. 9 shows the jet mill integrated with the deposition system including the chamber.

FIG. 10 illustrates a modified ESC gun design that minimizes accumulation of material inside the gun and improves uniformity of flow through the gun.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Disclosed herein are methods and apparatus for producing a coating on a substrate, beginning with electrostatic spray to deposit a base- or green-coating layer.

Two-Step Coating Processes—Overview

FIG. 1 illustrates a two-step process for producing a coating on a substrate.

The substrate **170** is placed in a deposition system **200**. One or more coating materials **150** are introduced into the deposition system **200**. These coating materials may be in dry powder or liquid suspension form, and may contain nano- or micro-sized particles or a combination of the two. Multiple materials may be combined together or introduced separately into the deposition system **200**. A variety of materials can be used, including nitrides, carbides, carbonitrides, borides, oxides, sulphides and silicides.

The deposition system **200** may use any of several methods to produce an initial coating or base layer on the substrate. One such deposition method is electrostatic spray coating (ESC), as described in U.S. Pat. No. 6,544,599 issued Apr. 8, 2003 to William D. Brown, et al., and U.S. Pat. No. 6,607,782 issued Aug. 19, 2003 to Ajay P. Malshe, et al. ESC deposition may be done as dry powder spray, or as liquid spray using a dispersion of the coating material in a suitable carrier liquid.

After the initial deposition step, dry solid particles of the coating material(s) are in contact with the substrate. The substrate with deposition **270** is the output of the deposition step **200** as illustrated in FIG. 1.

The substrate **270** with deposition of a base layer then undergoes a post-deposition treatment step **300**. Post-deposition treatment is used to bind the deposited dry particles to one another and to the substrate. Suitable treatment methods include:

Chemical vapor infiltration (CVI), which is similar to chemical vapor deposition (CVD) but using a slower reaction rate such that the binder infiltrates the porous dry powder deposition, coming into contact with both the substrate and the dry particles; and

3

Sintering, using any of several alternative sintering methods, singly or in combination, including:

- Microwave sintering
- Laser sintering
- Infrared sintering

Each of these methods applies one or more short bursts of high energy (microwave, laser, infrared, or high temperature and high pressure) to sinter the particles of the initial coating deposition, binding them to each other and to the substrate.

Another binding method is use of high temperature—high pressure (HT-HP), a process that is currently used for a variety of purposes including fabrication of polycrystalline cubic boron nitride (PCBN) solid compacts. In one embodiment of this invention, HT-HP is used as a post-deposition binding step to bind the deposited particles to each other and to the substrate.

In some embodiments, an additional treatment step (not shown in the figures) is applied after the post-deposition treatment step 300, to add an additional phase to the coating. One example of this is the use of electrostatic spray coating or ultrasonic spray deposition as a final step, after deposition and sintering of a base coating, for the purpose of applying active biological agents to the base coating. As a more specific example, a dental implant or other biomedical device, possibly with a porous surface layer, can be coated using ESC followed by microwave sintering of the base coating. Then in an additional post-sintering deposition step, an active agent can be applied, such as a biocidal or anti-bacterial agent, other active agents such as bone-morphogenic proteins, or particles carrying drugs for drug delivery at the surface of the device after implantation. These are just examples of how a post-processing step can be used to apply additional components to a base coating for specific purposes.

Other additional treatment steps (not shown in the figures) that can be applied after post-deposition treatment 300 can be used to enhance the binding of the coating and to reduce or eliminate defects and non-uniformities in the coating. For example, suitable treatments for hard coatings such as those used for cutting tools include high temperature—high pressure (HT-HP) and infrared sintering (pulsed infrared radiation). Other methods using transient energy sources also may be used to enhance the characteristics of the final coating on the substrate.

As shown in FIG. 2, some embodiments of the invention include an optional pre-deposition treatment step 100. Untreated coating materials 50 are treated prior to being passed as treated coating materials 150 to the deposition system 200. Pretreatment may be used to de-agglomerate the coating material particles. The pretreatment methods disclosed here can be used to treat materials prior to coating deposition, or for other purposes independent of any coating deposition system.

As a pre-processing step prior to deposition, the pre-treatment methods disclosed herein may be used for any one or more of the following purposes:

Fluidization, size discrimination and separation—fluidization helps maintain separation of dry powder particles, reduces agglomeration or clumping of particles, and allows preferentially feeding ultrafine particles or particles of smaller sizes; other methods for discriminating and preferentially feeding smaller particles also can be used.

De-agglomeration—it is well known that ultrafine particles and nanoparticles in particular have a tendency to clump together or agglomerate, forming clusters or ‘agglomerates’ that can be much larger than the base particle size. De-agglomerating the material helps

4

reduce the number and size of clusters, which helps to maintain beneficial characteristics of nanosized particles, and improves the uniformity and surface roughness of the final coating when desired based on the application.

Functionalization—particles can be functionalized for specific purposes.

Methods and Apparatus for Pre-Deposition Treatment

Various methods and apparatuses for pre-deposition treatment of materials are described here. These may be used alone, or with the various deposition methods/systems described herein.

Method and Apparatus for Fluidization

In one embodiment, dry powders consisting of nanoparticles, microparticles, or combinations thereof are fluidized using aerodynamic forces. FIG. 3 illustrates this. A fluidized bed (11) receives incoming powder via one or more powder inlet ports (7). The incoming powder may contain particles of different sizes, all of which are introduced to the fluidized bed. A supply of compressed air is provided through a suitable filter (1), flowmeter (2) and control valve (3) to the fluidizer air inlet (4). The control valve and flowmeter allow for control of the air flow rate. The air passes through a bed of silica beads (5), which help ensure uniform gas flow across the flow area and also act as a desiccant (the beads are replaced periodically). The air then passes through a porous fluidizer plate (6) and enters the chamber above where the powder is introduced at the inlet port (7).

The air flow rate is adjusted such that aerodynamic forces place the powder particles in motion, with smaller particles rising to the top of the fluidized bed (11). The result is a vertical gradient of average particle size over the height of the air flow column (8), with larger particles residing toward the bottom of the column and smaller particles residing toward the top. Multiple powder exit ports (9) are provided, allowing for adjustment of the size of particles to be drawn from the fluidizer. A powder pickup tube (10) is placed in one of the exit ports (9) to remove particles from the fluidizer. The unused ports are capped. The provision of multiple exit ports provides the capability for preferentially feeding ultrafine powder particles by adjusting the position of the powder pick-up tube (moving it from one exit port to another). In this method, the fraction of particles that are ultrafine must be balanced against deposition time due to the smaller mass flow rate of ultrafine particles.

In some embodiments, vibration also can be applied in combination with aerodynamic forces by incorporating vibrators (not shown) into the fluidizer. Vibration from the vibrators helps incite the additional movement of powder particles. The vibrators use mechanical vibrating energy created by a motor with an off-center mass rotating at high speed, or acoustical energy from sound waves.

Larger clusters of the powder accumulate at the bottom of the fluidized bed (11) and may be removed manually as part of a batch operation. For larger-scale operations, this may be automated by providing a powder removal and recycling capability.

Other Size Discrimination and Feeding Methods

Another method of discriminating the size of particles and preferentially feeding nano-sized or ultrafine particles is by

screening the powder using a micron sieve. A sieve (perforated plate or screen) can be used to screen out larger particles, collecting and feeding only the smaller particles based on the size of the openings in the sieve. This can be used as an option for any of the pre-deposition treatment methods described herein.

Still other methods for separating and feeding particles of a certain size range include use of gravity, buoyancy, and/or centrifugal forces to separate particles of different sizes. One example is to entrain the particles in a fluid stream (using air, nitrogen or other gas), and turn the direction of this stream such that larger particles are thrown to the outside where they are removed and recycled, while smaller particles are carried downstream to the deposition system 200. A second example is to create a low-velocity upward flow of particles entrained in a gas such that buoyancy tends to cause smaller particles to rise while larger particles tend to fall due to gravity forces exceeding buoyancy forces. Smaller particles are removed from the top or side and fed to the deposition system 200.

De-Agglomeration

Methods for de-agglomerating particles are described below. These may be applied independent of any deposition system. Some of these methods of de-agglomeration will be described later in conjunction with integrated pre-treatment and deposition methods, and apparatus for performing pre-treatment and deposition.

One method for de-agglomeration is use of a jet mill to break up clusters through impingement from a high-pressure gas jet. The gas may be air, nitrogen, or any of a variety of other suitable gases. FIG. 4 illustrates the jet mill. Dry powder enters the mill through a feed funnel (3). Two sources of air (or other gas) are provided, one as pushing air and the other as grinding air. Pushing air enters at the feed gas inlet (2), and it carries the incoming powder to the grinding chamber (6). Grinding air enters at the grinding air inlet (1) and is distributed around the chamber by the grind air manifold (7). Aerodynamic forces produced by the grinding air cause impact of the mixture of pushing air and powder particles against a solid wall or impingement pivots. This causes agglomerations to be broken apart, resulting in finer particles that collect at the center of the grinding chamber. These are picked up by the vortex finder (5), and the fine (or micronized) powder particles (4) then exit the mill via the powder outlet.

A second method for de-agglomeration is to disperse the particles in a liquid where the liquid has certain properties that promote dispersion and de-agglomeration. For example, we have used a solvent such as ethanol, combined with a surfactant that is "neutral" or bipolar. The liquid dispersion can be coupled with sonication to help achieve and maintain the desired dispersion of particles in the liquid. The liquid dispersion can be fed directly to the deposition system (e.g., for liquid ESC) or dried prior to feeding the material to the deposition system (e.g., for dry ESC).

A third method of de-agglomeration is to disperse the particles in a liquid as noted above, and then further de-agglomerating and drying the particles using an ultrasonic spray drying technique prior to feeding the dry powder to the deposition system. Ultrasonic spray drying involves use of an ultrasonic spray nozzle, which atomizes the liquid dispersion and in the process breaks up agglomerations through the action of the ultrasonic vibration. The droplets exit the ultrasonic nozzle and are then dried (e.g., via a cyclone dryer), evaporating the carrier liquid and leaving the fine particles behind in dry form. These are then carried in a gas stream to the deposition system. In addition to de-agglomerating the

particles, ultrasonic spray also helps produce particles of uniform size by creating droplets of uniform size.

A fourth method of de-agglomeration is to create an aerosol that is fed to the deposition system 200. FIG. 5 illustrates this, showing one suitable apparatus for creating an aerosol. Powder is dispersed in a liquid (see discussion above regarding choice of suitable liquids for dispersion) and stored in a pressurized fluid storage chamber (6). The chamber may be pressurized using an over-pressure of air, nitrogen, or other suitable gas. The pressurized liquid with entrained particles becomes an aerosol as it exits the chamber via the aerosol spray nozzle (5). The aerosol is then heated using heating coils (4) such that the liquid is evaporated, leaving dry particles in a powder spray (3). The powder spray from the aerosol unit is directly connected to the inlet of the ESC gun (1) for electrostatic deposition. The flowrate of the mixture may be adjusted by modifying the pressure and/or the nozzle flow characteristics. The speed of evaporation may be accelerated or retarded by adjusting the power to the heating coil.

Combinations of the above-described methods also may be used. For example, one combined method of de-agglomeration is to first disperse the particles in a liquid to break up tightly-bound agglomerates (see discussion above for desirable liquid properties), then remove the liquid to dry the particles (at which point they may tend to re-agglomerate but in loosely-bound clusters), and then use a jet mill as a final step to break up any loosely-bound agglomerates that formed during or after drying. We have used this method successfully for pre-deposition treatment of cubic boron nitride powder prior to electrostatic spray deposition (see discussion of integrated pre-treatment and deposition below). The method we have used involves specifically the following steps:

1. Disperse cBN powder received from the manufacturer in a mixture of ethanol and a neutral or bipolar surfactant, for example Zonyl (made by DuPont)—we have used a mass ratio of surfactant to powder of about 0.51~1.5%.
2. Manually stir the liquid suspension, and then use vibration or ultrasonication to further ensure a uniform dispersion.
3. Dry the mixture in a container on a hot plate. To speed up the drying and also prevent humidity incursion, apply a flushing gas (we have used nitrogen at 50-70 deg. C. with controlled humidity/dewpoint) through several nozzles located around the periphery of the open container. Manually stir the mixture during drying to reduce caking. Note that for scale-up to production levels, this operation could be automated.
4. Manually break up the resulting caked material using a mortar and pestle so that the result is a dry, loose powder that can be poured.
5. Pour the powder into the funnel of the jet mill, weighing the portions that are added so that the amount of material deposited can be controlled. For scale-up, this can be automated with a powder measurement unit (PMU).

For those methods that use liquid dispersion, the liquid dispersion can be coupled with sonication to help achieve and maintain the desired dispersion of particles in the liquid.

Functionalization

Functionalization of particles prior to deposition can allow coatings to be created for specific functions, or otherwise improve the characteristics of the resulting coating. Functionalization is typically realized by introducing a second phase or mixed phases of materials. For example, cubic boron nitride (cBN) particles can be over-coated with titanium nitride (TiN), titanium aluminum nitride (TiAlN), or alumi-

num oxide (Al₂O₃) to improve the flowability of cBN particles and to increase the resistance of the coating to oxidation (for the case of TiAlN overcoating). Functionalization also can introduce a guest material (such as silica in ultrafine particle size) that is stable and provides effective spacing between host material particles, reducing the chances of agglomeration. This will further help to improve powder coating surface quality such as surface roughness.

One method of functionalizing particles, including nanoparticles, microparticles, and combinations thereof, is to over-coat the particles with other materials chosen for specific functionality. A second method of functionalizing particles is to disperse them in a liquid containing a surfactant, where the carrier liquid and surfactant are chosen to provide a stable dispersion. The liquid dispersion can be fed to the deposition system **200** as a liquid dispersion (e.g., for liquid ESC) or dried prior to feeding the material to the deposition system (e.g., dry ESC). Liquid dispersion can be coupled with sonication to help achieve and maintain the desired dispersion of particles in the liquid.

Additional Pre-Deposition Treatment Methods

Other pre-deposition treatment methods also can be used for pre-processing the coating materials prior to deposition, either alone or in combination with the methods described above. For example, the powder can be pre-heated to help drive moisture prior to feeding the material. Ball milling also may be used to break up agglomerates and adjust the size of the powder particles provided to the deposition system.

Methods and Apparatus for Coating Deposition

FIG. 6 illustrates a deposition chamber that can be used for electrostatic spray coating (ESC) as well as other coating or deposition methods. A spray nozzle assembly (**1**) is mounted such that it sprays coating material (dry powder or liquid suspension containing particles) into the coating chamber (**2**). The spray nozzle assembly may employ electrostatic, ultrasonic, or ultrasonic plus electrostatic deposition means. The substrate(s) or part(s) to be coated are placed on a stage (**4**) that is suspended in the chamber using a stage suspension assembly (**3**). The orientation of the stage may be fixed or, as an option, a rotating stage may be used as described further herein. The distance between the stage and the spray nozzle can be adjusted.

The chamber is sealed so as to prevent egress of the coating material or ingress of contaminants. Material that is not deposited on the substrate(s) is collected in a powder recycling collector (**5**) so that material may be recycled. In the preferred embodiment, the unused material exits the sealed chamber via a liquid bath or other filtering means so that the material is captured for re-use and is prevented from being released to the environment.

In a preferred embodiment, the adjustments provided on the stage suspension assembly (**3**) are located external to the chamber by extending the assembly through the top of the chamber through openings that are sealed using O-ring type seals or other sealing means. With this design, adjustments in stage-to-nozzle distance can be made without opening the chamber.

FIG. 7 illustrates the rotating stage that is used as an option to improve uniformity of deposition across the surface of the substrate. The rotating stage can be used with electrostatic spray and other deposition methods. An electric motor (**1**) drives the apparatus through a reduction gear (**2**), causing the center shaft (**6**) to rotate. A sun plate (**7**) is attached to the

center shaft (**6**) and rotates with the shaft. A number of planetary gears (**5**) are mounted to the sun plate (**7**) using planetary shafts (**8**). The planetary gears mesh with an internal ring gear (**4**) that is mounted to the fixed mounting base (**3**). In one embodiment shown in the figure, six planetary gears are used.

As the sun plate rotates, the planetary gears move around the central axis of the assembly and, due to their interaction with the internal ring gear, the planetary gears also rotate on their own axes. Substrates are mounted on the individual planetary gear stages. The dual rotation action enhances the uniformity of the deposition on the substrate by ensuring that all points on the surface of the substrate are exposed equally to the material spray.

The planetary and ring gears can mesh using conventional gear teeth, or the planetary gears can be made as rollers that are pressed outward (e.g., by springs) such that the outer edge of each roller contacts the surface of the internal ring gear and friction causes the planetary gears to rotate.

For any type of electrostatic deposition, the planetary gears must be grounded in order to ground the substrate that is mounted on them. This requires that a means be provided to electrically connect the planetary gears to a grounded member. In one embodiment in which the planetary gears are rollers, the springs that press against the planetary gear shafts and hold the planetary gears against the internal ring gear also act as brushes to make an electrical connection between the planetary gears and the rest of the grounded rotating stage assembly.

The speed of the electric motor can be adjusted to ensure that the substrate to be coated is exposed to all parts of the deposition spray pattern equally in order to achieve the desired uniformity of coating. The speed can be adjusted by changing the power input (voltage) to the DC motor. In the specific embodiment shown in the figure, the ratio of the rotational speed of the planetary gears to that of the overall sun plate is fixed by the gear ratio. However, in alternative embodiments one or more additional motors or other means can be provided such that the two speeds can be adjusted independently.

The rotating stage also can be translated by mounting it on an appropriate platform that is moved laterally in either the x or the y direction, and the stage also can be translated in the z-axis direction (vertical direction in the figure), moving the rotating stage closer to or further away from the spray source.

Integrated Pre-Treatment and Deposition Methods and Apparatus

FIG. 8 illustrates an electrostatic spray coating (ESC) system integrated with a fluidizer for pre-deposition treatment of the powder. Compressed air, nitrogen or other suitable gas is fed to a set of pressure control valves. These valves control the air to the fluidizer and the feed air to the ESC gun. By combining fluidization with ESC deposition, agglomeration of the dry powder particles is reduced and ultrafine particles are preferentially fed to the ESC gun. This system has been used to provide uniform deposition of powders such as hydroxyapatite on substrates including titanium implants for biomedical applications. The system is suitable for use with many other materials and applications.

FIG. 9 illustrates an electrostatic spray coating (ESC) system with integrated jet mill for de-agglomeration of the incoming powder material. Compressed air, nitrogen or other suitable gas is provided to a set of pressure control valves. These valves control the feed air to the ESC gun, and both feed air and grinding air to the jet mill. Dry powder is fed to

the powder inlet of the jet mill. The grinding action of the jet mill breaks up agglomerates, and fine powder particles are carried by the feed air out of the jet mill directly to the ESC gun. Commercially-available jet mills typically incorporate a cyclone powder collector with a collection bag for capturing the milled powder. In this invention, the cyclone and bag are removed and a custom-designed coupling is used to connect the jet mill output directly to the input hose connection of the ESC gun. The pressure control valves are used to adjust the overall air pressure applied, and the relative pressures applied in grinding and 'pushing' (feed air) through the jet mill. This allows adjustment of the balance between pushing and grinding forces in the jet mill, and adjustment of the balance between aerodynamic forces and electrostatic forces during particle deposition in the ESC chamber. ESC guns typically use a much lower air pressure than is used in a jet mill. Electrostatic forces dominate the particle deposition. By coupling the jet mill directly to the ESC gun the aerodynamic forces play a much larger role. We have found that the increased aerodynamic forces provide a much more uniform coating deposition. This is likely due in part to the fact that the electrostatic field lines are not uniform at the substrate, due to non-uniformities in the surface characteristics of the substrate. The aerodynamic forces tend to overcome these non-uniformities by reducing the influence of electrostatic forces in the deposition. This result, significantly improving uniformity of deposition owing to increased aerodynamic forces relative to electrostatic forces, was unexpected. Integration of the jet mill with the ESC system provides de-agglomeration of the incoming powder particles, which by itself improves coating uniformity, and further improves uniformity of particle deposition through the increased influence of aerodynamic forces.

Other optional features that can be included in the system described here are:

Pre-heating of the carrier gas, when desired for specific applications;

Automatic feed of the powder material to the system, and automatic measurement of powder quantity (e.g., using a powder measurement unit) and other key variables such as temperature, pressure, etc.; also, automation of the substrate rotation/translation;

Use of a sieve as a further means of screening and separating particle sizes so that desired sizes of particles can be preferentially fed to the system;

Vibration and sloped surface design to help prevent accumulation of powder on feed surfaces;

Additional translation (in the x, y and/or z directions) of the substrate or ESC gun or both, to allow deposition on large surfaces; and

Use of multiple guns to allow coating large surfaces or complex geometries.

Commercially-available ESC guns can be used for the electrostatic spray coating systems described herein. However, the off-the-shelf guns commonly used for painting and powder coating have some disadvantages when applied for deposition of micro- and nano-sized particles. Specifically, the guns do not provide uniform flow within the passages internal to the gun, resulting in some spatial non-uniformity of the flow exiting the gun. Also, there are areas within the gun where powder tends to accumulate, which affects the ability to control the thickness of the deposition by controlling the mass of powder sent to the gun.

FIG. 10 illustrates a modified gun design that resolves these problems. Like the commercially available guns, air or other gas under pressure is provided to the gun along with a powder feed. An electrode (2) located at the nozzle exit

charges the particles as they exit the gun, producing a charged powder spray (1). However, in this case multiple powder feed inlets (4) are provided and they are angled in the direction of the flow, so that powder more easily joins the air flow path. In addition, by providing multiple inlets (three are provided in the example shown in the figure); powder is more uniformly distributed around the circumference of the flow path.

Also, two separate air inlets are provided. One is the booster air inlet (5), which provides the main feeding air for creating the electrostatic spray. In addition, air is provided to one or more vortex air inlets (3). In the example shown in the figure, two vortex air inlets are provided. These inlets are oriented such that air enters tangentially, creating a vortex within the ESC gun that helps to prevent powder accumulation on the surfaces of the nozzle body (6) and also helps maintain uniformity of the gas and powder mixture flow. The nozzle body is designed to have smooth surfaces with no crevices or cavities in which powder can accumulate.

We claim:

1. A method for coating a substrate with a deposition material comprising a powder, comprising the steps of:

(a) applying a pre-deposition treatment to the deposition material, wherein said applying a pre-deposition treatment step comprises a step of de-agglomerating the deposition material;

(b) directing the deposition material onto the substrate by means of electrostatic charging, wherein the deposition material is directed into a flow path of a nozzle of an electrostatic charging unit through a plurality of powder inlets positioned around the flow path of the nozzle, at least one powder inlet forming an acute angle with the flow path of the nozzle, wherein main feed air is directed into the flow path of a nozzle of the electrostatic charging unit through a booster air inlet positioned in the flow path at a position that is upstream of the position in the flow path of the plurality of powder inlets, and wherein additional air is directed tangentially into the nozzle through a plurality of vortex inlets downstream of the position in the flow path of the plurality of powder inlets, each vortex inlet connecting at a tangential angle to the nozzle, whereby a vortex is created within the nozzle by air entering the nozzle through the plurality of vortex inlets; and

(c) applying a sintering treatment to the substrate whereby the deposition material is adhered to the substrate.

2. The method of claim 1, wherein said directing the deposition material onto the substrate step further comprises the step of manipulating the substrate and wherein said manipulating substrate step comprises the step of rotating the substrate on a stage.

3. The method of claim 1, wherein the deposition material comprises at least one of the set comprising carbides, nitrides, carbonitrides, borides, oxides, sulfides, and silicides.

4. The method of claim 3, wherein the deposition material comprises boron nitride.

5. The method of claim 1, wherein said step of applying a sintering treatment comprises at least one of the set of microwave sintering, laser sintering, and infrared sintering.

6. The method of claim 1, wherein said pre-deposition treatment step comprises the step of fluidizing the deposition material.

7. The method of claim 6, wherein said pre-deposition treatment step comprises the step of fluidizing the deposition material aerodynamically wherein the deposition material is disposed as a fluidized bed on a fluidizer plate that receives a supply of compressed air passed through a desiccant and through the fluidizer plate.

11

8. The method of claim 7, wherein said fluidizing step further comprises the step of vibrating the deposition material.

9. The method of claim 7, wherein said fluidizing step comprises the step of sieving the deposition material.

10. The method of claim 1, wherein said de-agglomerating step is performed by means of a jet mill.

11. The method of claim 1, wherein said de-agglomerating step is performed by means of dispersing the deposition material in a non-aerosol dispersion liquid.

12. The method of claim 11, wherein said de-agglomerating step further comprises the step of applying sonication to the dispersion liquid.

13. The method of claim 11, wherein said de-agglomerating step further comprises the step of aerosolizing the dispersion liquid.

14. The method of claim 11, further comprising the step of applying an ultrasonic vibration to the dispersion liquid.

15. The method of claim 1, wherein said pre-deposition step further comprises the step of functionalizing the deposition material.

16. The method of claim 15, wherein said functionalization step comprises the step of overcoating the substrate.

17. The method of claim 15, wherein said functionalization step comprises the step of dispersing the deposition material in a mixture comprising a liquid and a surfactant.

12

18. The method of claim 17, further comprising the step of applying sonication to the mixture.

19. The method of claim 1, wherein the deposition material comprises micro-sized particles.

20. The method of claim 1, wherein the deposition material comprises nano-sized particles.

21. The method of claim 1, further comprising the step of directing an agent material to the substrate subsequent to said step of applying a sintering treatment to the substrate.

22. The method of claim 21, wherein the agent material comprises an active biological agent.

23. The method of claim 22, wherein the active biological agent comprises one of a biocidal and anti-bacterial agent.

24. The method of claim 21, wherein the agent material comprises a bone-morphogenic protein.

25. The method of claim 21, wherein the agent material comprises a drug-carrying agent.

26. The method of claim 1, wherein the booster air inlet is coaxial with the nozzle.

27. The method of claim 1, wherein the booster air inlet is configured to direct air in a direction toward an outlet of the nozzle.

* * * * *